AK Glass

Product Code: L06P-N2

Product Series: Coated Glass Fabric



Technical Data Sheet

PHYSICAL PROPERTIES

Coating Agent				Silane Coupling Agent
Type of Yarns	Warp yarn:			G150 1/0
	Weft yarn:			G150 1/0
		<u>SI</u>	<u>US</u>	Testing Standard
Fabric Weight		60 g/m ²	1.77 oz/yd ²	ASTM D3776
Weave Style		Plain		
CONSTRUCTION				
Density	Warp count:		24.0/in	ASTM D3775
Density	Warp count: Weft count:		24.0/in 22.0/in	ASTM D3775 ASTM D3775
Density	•			
Density Fabric Thickness	•	0.08 mm		
,	•	0.08 mm		ASTM D3775
,	•	0.08 mm		ASTM D3775
Fabric Thickness	•	0.08 mm 1000, 1270 mm	22.0/in	ASTM D3775

Quality Assurance

AK Glass Fabric is manufactured under a Quality Management System approved by ISO 9001

Packaging

AK Glass Fabrics are wound on 7cm diameter core, wrapped in stretch film, secured by bubble wrap, and packed in standard carton box.

Listed below are the standard box dimensions for specified fabric widths. All dimensions are internal measurements.

Fabric Width 1000mm: 21cm x 125cm x 21cm Fabric Width 1270mm: 21cm x 150cm x 21cm

Safety

Obtain, read, and understand the Material Safety Data Sheet (SDS) before use of AK Glass and AK Carbon Products FOR FURTHER INFORMATION, PLEASE CONTACT US



ASIA KANGNAM COMPANY LIMITED

69/1 Moo 6, Tambol Thakam, Amphur Bangpakong, Chachoengsao, 24130 Thailand Phone: (+66) 38 573 635

Fax: (+66) 38 573 636, (+66) 38 573 734

This information and data contained herein is offered solely as a guide in the selection of a reinforcement material. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. The values listed for weight, thickness, and breaking strength are greige values, unless otherwise noted. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose.

Spec number: CU-PD-CO-080 Date: April 20, 2018 Rev. 00